

HELAVIA® standard sleeves in polychloroprene rubber for SES® sleeve process



HELAVIA®




HELAVIA

Material:	polychloroprene rubber quality 3490
Operating temperatures:	-30 to +90°C (+110°C short time)
Hardness shore A:	40 ±5
Tensile strength at break:	>6,5 MPa
Ultimate elongation:	>500 %
Tear strength:	>10 kN/m
Dielectric strength:	>13 kV/mm
Volume resistivity:	4x10 ⁹ Ω.cm
Flame resistance:	V0 UL94
Lubricated sleeves:	until type A4



Standard colour:

010
black

type	article number	for wires Ø (mm)	length mm	Ø int. mm	wall thickness mm	
A0-M	0201 0071 010	1,25 - 2	20	1,25	0,5	1000
A0-C	0201 0001 010					100
A1-M	0201 0072 010	1,75 - 3,5	20	1,75	0,5	1000
A1-C	0201 0002 010					100
A1bis-M	0201 0073 010	2,4 - 4,5	20	2,4	0,6	1000
A1bis-C	0201 0003 010					100
A1K*-M	0201 0081 010	2,5 - 5,5	25	2,5	0,9	1000
A1K*-C	0201 0011 010					100
A2-M	0201 0074 010	3 - 6	25	3	0,6	1000
A2-C	0201 0004 010					100
A2K*-M	0201 0082 010	4 - 8	30	4	1,2	1000
A2K*-C	0201 0012 010					100
A3-M	0201 0075 010	5 - 9	25	5	0,7	1000
A3-C	0201 0005 010					100
A4-M	0201 0076 010	7,5 - 12	30	7,5	0,8	1000
A4-C	0201 0006 010					100
A5-D	0201 0077 010	10 - 15	35	10	0,9	500
A5-C	0201 0007 010					100
A8-D	0201 0078 010	12 - 20	50	12	1,2	500
A8-C	0201 0008 010					100
A9-D	0201 0079 010	14 - 23	50	14	1,3	500
A9-C	0201 0009 010					100
A10-D	0201 0080 010	17 - 28	50	17	1,3	500
A10-C	0201 0010 010					100

* thick-walled sleeves.

